

**Slip Check to AS 4586-2013
600x600 Silver Stone 20mm
TK26602MG**

Report Number: R23565b

Report Date: 18 May 2021

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports


Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

Trend Tile Pty Ltd
10 Rousell Road
Eastern Creek NSW 2766

Approved by



Dale Rowell
Authorised Signatory

18 May 2021

Test Report No. R23565b

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Trend Tile Pty Ltd
 Client Address: 10 Rousell Road
 Eastern Creek NSW 2766
 Product Manufacturer: Eastwide
 Product Description: 600x600 Silver Stone 20mm TK26602MG

Test conducted according to: AS 4586:2013 Appendix A
 Location: 4/40 Bessemer Street, Blacktown NSW 2148
 Conducted by: Alex Jovanovic

Date: 17 May 2021 Temperature: 19°C
 Sample: Unfixed Cleaning: None
 Rubber slider used: Slider 96 Conditioned: Grade P 400 paper dry followed
 Slope of specimen: Tested on a flat level surface by wet lapping film
 Direction of Test: NA

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	67	65	64	63	63

Reported SRV of Sample:	64
Class:	P5

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd