



National Ceramic Industries Australia Pty Ltd
175 Racecourse Rd, Rutherford NSW 2320
PO Box 765 Maitland NSW 2320
Tel: 02 49318400 Fax: 02 49318499
ABN 83 100 467 267
www.ncia.com.au

Att Trend Tile

Attached are independent test results of NCIA's standard matt glaze and standard P5 external. These reports are appropriate for the Waikiki series internal and external. Batch testing will be performed at the factory during production and specific batch results are available on request"

Slip Check to AS 4586-2013 NCIA Matt

Report Number: R20306-2b

Report Date: 18 February 2020

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports


Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

NCIA
175 Racecourse Road
Rutherford NSW 2320

Approved by



Dale Rowell
Authorised Signatory

18 February 2020

Test Report No. R20306-2b

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: NCIA
 Client Address: 175 Racecourse Road
 Rutherford NSW 2320

Product Manufacturer: NCIA
 Product Description: NCIA Matt

Test conducted according to: AS 4586:2013 Appendix A
 Location: 4/40 Bessemer Street, Blacktown NSW 2148
 Conducted by: Yuliana Vargolomova

Date:	31 January 2020	Temperature:	28-29°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	NA		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	26	30	29	34	28

Reported SRV of Sample:	29
Class:	P2

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd